

Technical Data Sheet

H2938P

ABS

PRODUCT DESCRIPTION:

ABSH2938P is a medium heat resistance ABS resin for plating, offering high rigidity and high impact.

FEATURES:

- High rigidity
- High impact

APPLICATION:

- IP cluster trim and bezel
- Rear-view mirror housing

Properties	Standard	Condition	Unit	Typical Value
Physical				
Density	ISO 1183	23°C	g/cm ³	1.05
Mold Shrinkage	ISO 294	23°C, 48hr	%	0.4-0.7
Mechanical				
Tensile Strength	ISO 527	50mm/min	MPa	43
Flexural Strength	ISO 178	2mm/min	MPa	65
Flexural Modulus	ISO 178	2mm/min	MPa	2200
Notched Izod Impact	ISO 180	5.5J, 23°C	kJ/m ²	24
Notched Charpy Impact	ISO 179	4J, 23°C	kJ/m ²	25
Notched Charpy Impact	ISO 179	4J, -30°C	kJ/m ²	12
Thermal				
Heat Deflection Temperature	ISO 75	120°C/hr, 0.45MPa	°C	102
Heat Deflection Temperature	ISO 75	120°C/hr, 1.80MPa	°C	95
Vicat Softening Temperature	ISO 306	50°C/hr, 5kg	°C	105
Other Properties				
Flammability	ISO 3795	355×100×3 mm	mm/min	≤80

Processing Parameters		Value	Unit
Pre-treatment			
Drying Temperature		80 ~ 90	°C
Drying Time		3 ~ 4	hour
Maximum Moisture Content		≤0.05	%
General Guidelines			
Barrel Temperature	Rear	200 ~ 220	°C
	Middle	220 ~ 240	°C
	Front	235 ~ 250	°C
Nozzle		240 ~ 250	°C
Melt Temperature		230 ~ 250	°C
Mold Temperature		50 ~ 80	°C

Note :

1. Values are measured at 23°C and in RH of 50% on injection molded specimens.
2. Typical values for uncolored products, not specifications, and may vary slightly with different colors.
3. Flexural strength is tested with fixed deflection.
4. HDT: specimens are unannealed.
5. The general guidelines are only for reference. Exact settings have to follow the product and machine conditions.

Disclaimer :

To the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the data compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials, or process described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. You may not copy this document to a web site.

Kumho-Sunny expressly disclaim liability for any loss, damage, or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. There is no endorsement of any product or process, and we expressly disclaim any contrary implication.